



报告编号/Report Reference No.:
NTEK- 2015DC1026025S

UN38.3 检测报告

UN38.3 Test Report

产品名称: 锂离子聚合物电池 PR-2874E9G

Name of Samples: Lithium-ion Polymer Battery PR-2874E9G

委托单位: 惠州 TCL 金能电池有限公司

Client: TCL Hyperpower Batteries Inc

生产单位: 惠州 TCL 金能电池有限公司

Manufacturer: TCL Hyperpower Batteries Inc

签发日期:
2015-11-04

Date of issue:

深圳市北测检测技术有限公司
Shenzhen NTEK Testing Technology Co., Ltd.

Client 委托单位	TCL Hyperpower Batteries Inc 惠州 TCL 金能电池有限公司
Address 地址	No. 3, Hechang Dong Six Rd., Huitai Industrial Zone, Huicheng District, Huizhou City, Guangdong Province, China 广东省惠州市惠城区仲恺开发区惠台工业区和畅东六路 3 号
Manufacturer 制造商	TCL Hyperpower Batteries Inc 惠州 TCL 金能电池有限公司
Address 地址	No. 3, Hechang Dong Six Rd., Huitai Industrial Zone, Huicheng District, Huizhou City, Guangdong Province, China 广东省惠州市惠城区仲恺开发区惠台工业区和畅东六路 3 号
Name of samples 样品名称	Lithium-ion Polymer Battery 锂离子聚合物电池
Model/type reference 型号	PR-2874E9G
Trademark 商标	-
<p>Tested according to 测试依据:</p> <p>Amendments to the Fifth Revised Edition of the Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria, section 38.3 lithium batteries (ST/SG/AC.10/11/Rev.5/Amend.2 section 38.3). 联合国《关于危险货物运输的建议书, 试验和标准手册》, 第五修订版修正 2, 第三部分, 38.3 节锂电池要求 (ST/SG/AC.10/11/Rev.5/Amend.2 第 38.3 节)</p>	
<p>Test items 测试项目:</p> <p>Test T.1: Altitude simulation 测试 T.1 高度模拟 Test T.5: External short circuit 测试 T.5 外部短路 Test T.2: Thermal Test 测试 T.2 温度试验 Test T.6: Crush 测试 T.6 挤压 Test T.3: Vibration 测试 T.3 振动 Test T.7: Overcharge 测试 T.7 过度充电 Test T.4: Shock 测试 T.4 冲击 Test T.8: Forced discharge 测试 T.8 强制放电</p>	
<p>Test Conclusion 测试结论:</p> <p>The Lithium-ion Polymer Battery submitted by TCL Hyperpower Batteries Inc is tested according to Section 38.3 of Amendments to the Fifth Revised Edition of the Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria (ST/SG/AC.10/11/Rev.5/Amend.2).</p> <p>Test results: PASS</p> <p>由惠州 TCL 金能电池有限公司提交的锂离子聚合物电池按照联合国《关于危险货物运输的建议书, 试验和标准手册》, 第五修订版修正 2, 第三部分, 38.3 节锂电池要求(ST/SG/AC.10/11/Rev.5/Amend.2 第 38.3 节)进行测试。</p> <p>测试结果: 合格</p>	
Tested by: 主检人: 邱嘉文	<p>Reviewed by: 审核人: [Signature]</p> <p>Approved by: 批准人: [Signature]</p> <p>Seal of NTEK TESTING TECHNOLOGY CO., LTD. APPROVED</p> <p>报告单位 (盖章)</p>

Sample Description 样品描述:			
Nominal Voltage 标称电压	3.8V	Rated Capacity 额定容量	4500mAh (17.1Wh)
Standard Charging Current 标准充电电流	900mA (0.2C)	Max. Continuous Charging Current 最大充电电流	3000mA
Limited Charging Voltage 充电限制电压	4.35V	Cut-Off Voltage 放电截止电压	3.0V
Max. Discharge Current 最大放电电流	3000mA	Number of cell 电芯数量	Single cell 单电芯
Rated Capacity of Cell 电芯额定容量	4500mAh	Appearance of Samples 样品外观	Silvery and Prismatic 棱柱形、银色
Classification of Samples 样品类型	Small Lithium ion Cells 小型锂离子电芯	Size of battery (T×W×L) 电池尺寸	2.86×73.6×155.0mm

Receiving Date 接收日期	2015-10-22	Completing Date 完成日期	2015-11-04
------------------------	------------	-------------------------	------------

Remarks 备注说明:

Batteries of A1#-A10# are fully charged at first cycle;
 Component cells of A11#-A15# at 50% of the design rated capacity at first cycle;
 Batteries of A16#-A19# are fully charged at first cycle;
 Batteries of A20#-A23# are fully charged after 50 cycles;
 Component cells of A24#-A33# at first cycle in fully discharged states;
 Component cells of A34#-A43# are fully discharged after 50 cycles;
 Test environment condition: ambient temperature: 15-25℃, ambient humidity: 40-70%
 电池 A1#-A10#为一次循环满电状态;
 元件电池芯 A11#-A15#为一次循环后 50%充电状态;
 电池 A16#-A19#为一次循环满电状态;
 电池 A20#-A23#为 50 个循环满电状态;
 元件电池芯 A24#-A33#为一次循环完全放电状态;
 元件电池芯 A34#-A43#为 50 个循环完全放电状态;
 试验环境条件: 环境温度: 15-25℃, 环境湿度: 40-70%

Summaries of testing 测试摘要:

Each battery type is subjected to tests T.1 to T.8. Tests T.1 to T.5 are conducted in sequence on the same battery. Tests 6 and 8 are conducted using not otherwise tested batteries. Test T.7 may be conducted using undamaged batteries previously used in Tests T.1 to T.5 for purposes of testing on cycled batteries.
 每一种类型的电池均应进行T.1至T.8项试验。电池必须按顺序在相同的一组电池上进行试验T.1至T.5。试验T.6和T.8应使用未另外试验过的电池。试验T.7可以使用先前在试验T.1至T.5中使用过的未损坏电池进行,以便测试进行在循环过的电池上。

In order to quantify the mass loss, the following procedure is provided:

$$\text{Mass loss(\%)} = (M_1 - M_2) / M_1 \times 100$$

为了量化质量损失，可用以下公式计算：

$$\text{质量损失(\%)} = (M_1 - M_2) / M_1 \times 100$$

Where M_1 is the mass before the test and M_2 is the mass after the test. When mass loss does not exceed the values in Table below, it is considered as "no mass loss".

式中： M_1 是试验前的质量， M_2 是试验后的质量。如果质量损失不超过下表所列的数值，应视为“无质量损失”。

Mass M of cell or battery 电芯或电池的质量	Mass loss limit 质量损失限值
$M < 1\text{g}$	0.5%
$1\text{g} \leq M \leq 75\text{g}$	0.2%
$M > 75\text{g}$	0.1%

In test T.1 to T.4, batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

在测试T.1至T.4中，电池须满足无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。

Test equipments 检测设备:

N170 Battery test system 电池检测系统

N171 Electronic balance 电子天平

N172 Low pressure chamber 低气压试验箱

N077 Programmable Temperature & Humidity Controller 可编程恒温恒湿箱

N173 Vibration test system 振动测试系统

N174 Hydraulic Hoist Vertical Shock System 液压垂直冲击系统

N175 Short circuit tester 短路测试机

N177 Explosion-proof chamber 防爆箱


N178 DC Source 直流电源

N180 Digital multimeter 数字式万用表



N185 uR1000 recorder uR1000 记录仪

N179 Battery crush and acupuncture tester 电池挤压针刺试验机


Test Procedure 测试程序




Photos of sample 样品照片



Photos of sample 样品照片



Photos of sample 样品照片



Test results 测试结果:

Test T.1: Altitude simulation 测试T.1: 高度模拟

Test method 测试方法

Batteries are stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature ($20 \pm 5^\circ\text{C}$).
试验电池被放置在压力等于或低于11.6 kPa和环境温度($20\pm 5^\circ\text{C}$)下存放至少6小时。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火，并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。

Test Data showed in table below 测试数据见下表

State of sample 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/ voltage pre-test (%) 试验后电压/ 试验前电压	Results 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
at first cycle, in fully charged states 一次循环后满电状态	A1#	69.739	4.33	69.739	4.33	0.00	100.0	PASS 合格
	A2#	70.188	4.33	70.188	4.33	0.00	100.0	PASS 合格
	A3#	70.010	4.33	70.010	4.33	0.00	100.0	PASS 合格
	A4#	70.340	4.33	70.340	4.33	0.00	100.0	PASS 合格
	A5#	69.629	4.33	69.629	4.33	0.00	100.0	PASS 合格
	A6#	69.489	4.33	69.489	4.33	0.00	100.0	PASS 合格
	A7#	70.461	4.33	70.461	4.32	0.00	99.77	PASS 合格
	A8#	70.227	4.33	70.227	4.33	0.00	100.0	PASS 合格
	A9#	69.903	4.33	69.903	4.33	0.00	100.0	PASS 合格
	A10#	70.307	4.33	70.307	4.33	0.00	100.0	PASS 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.

测试后，电池未渗漏、未泄气、未解体、未破裂和未起火。

Shenzhen NTEK Testing Technology Co., Ltd.

Tel: (86)-0755-61156588 Fax: (86)-0755-61156599

Web: www.ntek.org.cn

Ambient temperature 环境温度: 24.1°C

Test T.2: Thermal test 测试T.2: 温度试验

Test method 测试方法

Batteries are to be stored for at least six hours at a test temperature equal to $72 \pm 2^\circ\text{C}$, followed by storage for at least six hours at a test temperature equal to $-40 \pm 2^\circ\text{C}$. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated 10 times, after which all test batteries are to be stored for 24 hours at ambient temperature ($20 \pm 5^\circ\text{C}$).

电池放置在试验温度等于 $72 \pm 2^\circ\text{C}$ 的条件下存放至少6小时, 接着再在试验温度等于 $-40 \pm 2^\circ\text{C}$ 的条件下存放至少6小时。两个极端试验温度之间的最大时间间隔为30分钟。此程序重复进行, 共完成10次, 接着将所有试验电池在环境温度($20 \pm 5^\circ\text{C}$)下存放24小时。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火, 并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。

Test Data showed in table below 测试数据见下表

State of sample 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/ voltage pre-test (%) 试验后电压/ 试验前电压	Results 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
at first cycle, in fully charged states 一次循环后满电状态	A1#	69.739	4.33	69.718	4.30	0.042	99.31	PASS 合格
	A2#	70.188	4.33	70.167	4.30	0.043	99.31	PASS 合格
	A3#	70.010	4.33	69.987	4.31	0.034	99.54	PASS 合格
	A4#	70.340	4.33	70.317	4.30	0.043	99.31	PASS 合格
	A5#	69.629	4.33	69.605	4.29	0.034	99.08	PASS 合格
	A6#	69.489	4.33	69.468	4.30	0.042	99.31	PASS 合格
	A7#	70.461	4.32	70.437	4.28	0.034	99.07	PASS 合格
	A8#	70.227	4.33	70.201	4.31	0.034	99.54	PASS 合格
	A9#	69.903	4.33	69.881	4.30	0.042	99.31	PASS 合格

	A10#	70.307	4.33	70.283	4.29	0.032	99.08	PASS 合格
--	------	--------	------	--------	------	-------	-------	------------

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.

测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

Ambient temperature 环境温度: 24.0°C

Test T.3: Vibration 测试T.3: 振动

Test method 测试方法

Batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.

The logarithmic frequency sweep is as follows: from 7 Hz a peak acceleration of 1 g_n is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 g_n occurs (approximately 50 Hz). A peak acceleration of 8 g_n is then maintained until the frequency is increased to 200 Hz.

电池紧固于振动台台面, 但不得造成电池变形, 并能准确可靠地传播振动。振动应是正弦波形, 对数扫描频率在 7 Hz和200 Hz之间, 再回到7 Hz, 1次循环时间为15分钟。这一振动过程须对三个互相垂直的电池安装方位的每一方向重复进行12次, 总共为时3小时。其中一个振动方向必须与端面垂直。

对数扫频方式: 从7 Hz开始, 保持1 g_n 的最大加速度, 直到频率达到18 Hz。然后将振幅保持在0.8mm (总位移1.6mm), 并增加频率直到峰值加速度达到8 g_n (频率约为50 Hz)。将峰值加速度保持在8 g_n 直到频率增加到200 Hz。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火, 并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。

Test Data showed in table below 测试数据见下表

State of sample 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss 质量损失 (%)	Voltage after test/ voltage pre-test (%) 试验后电压/ 试验前电压	Results 结果
		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)			
at first cycle, in fully charged states 一次循环后满电	A1#	69.718	4.30	69.718	4.30	0.00	100.0	PASS 合格
	A2#	70.167	4.30	70.167	4.30	0.00	100.0	PASS 合格

状态	A3#	69.987	4.31	69.987	4.31	0.00	100.0	PASS 合格
	A4#	70.317	4.30	70.317	4.30	0.00	100.0	PASS 合格
	A5#	69.605	4.29	69.605	4.29	0.00	100.0	PASS 合格
	A6#	69.468	4.30	69.468	4.30	0.00	100.0	PASS 合格
	A7#	70.437	4.28	70.437	4.28	0.00	100.0	PASS 合格
	A8#	70.201	4.31	70.201	4.31	0.00	100.0	PASS 合格
	A9#	69.881	4.30	69.881	4.30	0.00	100.0	PASS 合格
	A10#	70.283	4.29	70.283	4.29	0.00	100.0	PASS 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.

测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

Ambient temperature 环境温度: 24.2℃

Test T.4: Shock 测试 T.4: 冲击

Test method 测试方法

Batteries are secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery. Each battery is subjected to a half-sine shock of peak acceleration of 150 g_n and pulse duration of 6 milliseconds. Each battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the battery for a total of 18 shocks.

试验电池用刚性支架紧固在试验装置上, 支架支撑着每个试验电池组的所有安装面。每个电池须经受峰值加速度 150 g_n和脉冲持续时间6 ms的半正弦波冲击。每个电池须在三个互相垂直的电池安装方位的正方向经受三次冲击, 接着在反方向经受三次冲击, 总共经受18次冲击。

Requirement 要求

Batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电池须无渗漏、无泄气、无解体、无破裂和无起火, 并且每个试验电池在试验后的开路电压不小于其在进行这一试验前电压的90%。

Test Data showed in table below 测试数据见下表

State of sample 样品状态	No. 编号	Pre-test 试验前		After test 试验后		Mass loss	Voltage after test/ voltage	Results 结果
		Mass	Voltage	Mass	Voltage			

		质量 (g)	电压 (V)	质量 (g)	电压 (V)	质量损 失 (%)	pre-test (%) 试验后电压/ 试验前电压	
at first cycle, in fully charged states 一次循环后满电 状态	A1#	69.718	4.30	69.718	4.30	0.00	100.0	PASS 合格
	A2#	70.167	4.30	70.167	4.30	0.00	100.0	PASS 合格
	A3#	69.987	4.31	69.987	4.31	0.00	100.0	PASS 合格
	A4#	70.317	4.30	70.317	4.30	0.00	100.0	PASS 合格
	A5#	69.605	4.29	69.605	4.29	0.00	100.0	PASS 合格
	A6#	69.468	4.30	69.468	4.30	0.00	100.0	PASS 合格
	A7#	70.437	4.28	70.437	4.28	0.00	100.0	PASS 合格
	A8#	70.201	4.31	70.201	4.31	0.00	100.0	PASS 合格
	A9#	69.881	4.30	69.881	4.30	0.00	100.0	PASS 合格
	A10#	70.283	4.29	70.283	4.29	0.00	100.0	PASS 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire.

测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

Ambient temperature 环境温度: 24.1°C

Test T.5: External short circuit 测试T.5 外部短路

Test method 测试方法

Batteries to be tested are temperature stabilized so that its external case temperature reaches $55 \pm 2^\circ\text{C}$ and then the battery are subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at $55 \pm 2^\circ\text{C}$. This short circuit condition is continued for at least one hour after the battery external case temperature has returned to $55 \pm 2^\circ\text{C}$. The battery is observed for a further six hours for the test to be concluded.

试验电池在测试温度下放置至稳定状态, 使其外壳温度达到 $55 \pm 2^\circ\text{C}$, 然后使电池在 $55 \pm 2^\circ\text{C}$ 下经受总外电阻小于 0.1Ω 的短路条件。短路测试持续到电池外壳温度回到 $55 \pm 2^\circ\text{C}$ 后继续至少1小时。试验电池被观察6小时再下结论。

Requirement 要求

Batteries meet this requirement if their external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire within six hours after test.

电池外壳温度不超过 170°C , 并且在试验过程中及试验后6小时内无解体、无破裂, 无起火。

Test data showed in table below 测试数据见下表

State of sample 样品状态	No. 编号	The Highest temperature 电池表面最高温度 (°C)	Results 结果
at first cycle, in fully charged states 一次循环后满电状态	A1#	57.3	PASS 合格
	A2#	56.8	PASS 合格
	A3#	57.3	PASS 合格
	A4#	57.2	PASS 合格
	A5#	57.1	PASS 合格
	A6#	56.9	PASS 合格
	A7#	57.0	PASS 合格
	A8#	57.2	PASS 合格
	A9#	57.0	PASS 合格
	A10#	56.9	PASS 合格

Notes 注释:

There is no disassembly, no rupture and no fire within six hours after test.

电池在测试后 6 小时内未解体、未破裂，未起火。

Ambient temperature 环境温度: 23.9°C

Test T.6: Crush 测试T.6: 挤压

Test method 测试方法

A component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

- (a) The applied force reaches 13 kN \pm 0.78 kN;
- (b) The voltage of the cell drops by at least 100 mV; or
- (c) The cell is deformed by 50% or more of its original thickness.

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

A prismatic or pouch cell shall be crushed by applying the force to the widest side.

Shenzhen NTEK Testing Technology Co., Ltd.

Tel: (86)-0755-61156588 Fax: (86)-0755-61156599

Web: www.ntek.org.cn

Each component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using component cells that have not previously been subjected to other tests.

将元件电池芯放在两个平面之间挤压，挤压力度逐渐加大，在第一个接触点上的速度大约为 1.5 cm/s。挤压持续进行，直到出现以下三种情况之一：

- (a) 施加的力量达到 $13 \text{ kN} \pm 0.78 \text{ kN}$;
- (b) 电芯的电压下降至少 100mV; 或
- (c) 电芯形变达原始厚度的 50%或更多。

一旦达到最大压力、电压下降 100mV 或更多，或电芯形变至少达原厚度的 50%，即可解除压力。

棱柱形或袋装电池须从最宽的面施压。

每个试样元件电池芯只做一次挤压试验。试样须继续观察 6 小时。试验须使用之前未做过其他试验的元件电池芯进行。

Requirement 要求

Component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire within six hours after the test.

元件电池芯外壳温度不超过 170°C ，并且在试验过程中及试验后6小时内无解体，无起火。

Test data showed in table below 测试数据见下表

State of sample 样品状态	No. 编号	The Highest temperature 电池表面最高温度 ($^{\circ}\text{C}$)	Results 结果
at first cycle at 50% of the design rated capacity 一次循环后 50%充电 状态	A11#	25.8	PASS 合格
	A12#	25.9	PASS 合格
	A13#	25.6	PASS 合格
	A14#	25.8	PASS 合格
	A15#	26.0	PASS 合格

Notes 注释:

There is no disassembly, no rupture and no fire within six hours after test.

电池在测试后 6 小时内未解体、未起火。

Ambient temperature 环境温度: 23.5°C

Test T.7: Overcharge 测试 T.7: 过度充电

Test method 测试方法

The charge current is twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

- (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of

the test is the lesser of two times the maximum charge voltage of the battery or 22V.

Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours.

充电电流为制造商建议的最大持续充电电流的两倍。试验的最小电压如下:

- (a) 制造商建议的充电电压不大于18伏时, 试验的最小电压应是电池组最大充电电压的两倍或22伏两者中的较小者。

试验应在环境温度下进行。进行试验的时间应为24小时。

Requirement 要求

Batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

电池在试验过程中和试验后7天内无解体, 无起火。

Test data showed in table below 测试数据见下表

Overcharge current: 过充电电流: 2×3000=6000mA	Overcharge voltage: 过充电电压: 2×4.35=8.7V	Total time of charging: 过充试验时间: 24 hours
State of sample 样品状态	No. 编号	Results 结果
at first cycle, in fully charged states 一次循环后满电状态	A16#	PASS 合格
	A17#	PASS 合格
	A18#	PASS 合格
	A19#	PASS 合格
after fifty cycles ending in fully charged states 50 次循环后满电状态	A20#	PASS 合格
	A21#	PASS 合格
	A22#	PASS 合格
	A23#	PASS 合格

Notes 注释:

There is no disassembly and no fire during the test and within seven days after the test.

电池在测试中和测试后 7 天内未解体, 未着火。

Ambient temperature 环境温度: 23.7℃

Test T.8: Forced discharge 测试 T.8: 强制放电

Test method 测试方法

Each component cell is forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.

Shenzhen NTEK Testing Technology Co., Ltd.

Tel: (86)-0755-61156588 Fax: (86)-0755-61156599

Web: www.ntek.org.cn

The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell is forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

每个元件电池芯在环境温度下与 12V 直流电电源串联在起始电流等于制造商给定的最大放电电流的条件下强制放电。

元件电池芯与一个适当大小的电阻负载串联以调节到规定大小的放电电流。每块电芯的放电时间（单位为 h）等于电芯的额定容量除以试验初始放电电流（单位 A）。

Requirement 要求

Component cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

元件电池芯在试验过程中和试验后 7 天内无解体，无起火。

Test data showed in table below 测试数据见下表

Discharge current: 强制放电电流: 3000mA	Test voltage: 试验电压: 12Vdc	Total time of discharging: 试验时间: 90 Minutes
State of sample 样品状态	No. 编号	Results 结果
at first cycle, in fully discharged states 一次循环完全放电状态	A24#	PASS 合格
	A25#	PASS 合格
	A26#	PASS 合格
	A27#	PASS 合格
	A28#	PASS 合格
	A29#	PASS 合格
	A30#	PASS 合格
	A31#	PASS 合格
	A32#	PASS 合格
after fifty cycles ending in fully discharged states 50 个循环完全放电状态	A33#	PASS 合格
	A34#	PASS 合格
	A35#	PASS 合格
	A36#	PASS 合格

	A37#	PASS 合格
	A38#	PASS 合格
	A39#	PASS 合格
	A40#	PASS 合格
	A41#	PASS 合格
	A42#	PASS 合格
	A43#	PASS 合格

Notes 注释:

There is no disassembly and no fire during the test and within seven days after the test.

电池在测试中和测试后 7 天内未解体, 未着火。

Ambient temperature 环境温度: 23.7℃

*****End of Test Report 检测报告结束*****

Important 注意事项

1. The test report is invalid without the official stamp of NTEK and Paging seal of NTEK.
本报告书无本公司公章、骑缝章无效。
2. Nobody is allowed to photocopy or partly photocopy this test report without written permission of NTEK.
未经本公司书面同意，不得部分地复制本报告书。
3. The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer.
本报告书无批准人、审核人、及主检人签名无效。
4. The report is invalid when anything of following happens – illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.
私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。
5. Objections to the test report must be submitted to NTEK within 15 days.
对报告书若有异议，应于收到报告之日起15天内向本公司提出。
6. The test report is valid for the tested samples only.
本报告仅对测试样品有效。
7. The Chinese contents in this report are only for reference.
本报告中的中文内容仅供参考。

深圳市北测检测技术有限公司

Shenzhen NTEK Testing Technology Co., Ltd.

地址：深圳市宝安区西乡三围奋达科技园 E 栋 1 楼

Address: 1/F, Building E, Fenda Technology Park, Sanwei, Xixiang Town, Baoan District, Shenzhen City

Tel: (0755)61156568

Fax: (0755)61156599

Email: coco@ntek.org.cn Kevin@ntek.org.cn

www.ntek.org.cn