

Murata Energy Device Wuxi Co., Ltd.

No.27, Changjiang Road, New District, Wuxi, Jiangsu Province, 214028 P.R.C

Phone: 86-510-8523-9120

Page: 1 of 7

リチウムイオン電池認証書（類似機種用）

Lithium-ion cell or battery
Certification for Similar Models

No: MDW-PC1825

Date: 2018.12.25

1. ☐単電池 / ☐single cell ☐single cell battery

■組電池 / battery(pack) (セル構成 / composition of cell : 1P3S)

2. 機種名 / customer model name : AP18K4K Murata model name : LIS3120

3. 顧客名 / customer : ACER

4. 定格 / rated

項目 / item	規格値 / specification	備考 / remarks
公称電圧 / nominal voltage	11.4V	
定格容量 / rated capacity	3880mAh	
ワット時定格値(Wh) / Watt-hour rating	44Wh	単電池 / cells ≤ 20Wh 組電池 / batteries ≤ 100Wh

5. 類似機種及び試験結果 / Similar Model and Test Result

1) 類似機種名 / Similar Model (Murata model name) : LIS3119(11.4V 3880mAh 44Wh)

2) 試験結果 / Test Result

国連勧告テスト結果 / Test results of the UN Recommendations on the Transport of Dangerous Goods

国連勧告テスト及び判定基準 (38.3 リチウム電池)		テスト結果 / test results	備考 / remarks
NO	テスト項目 test item		
T1	高度シミュレーション / Altitude simulation	OK	
T2	温度試験 / Thermal test	OK	
T3	振動 / Vibration	OK	
T4	衝撃 / Shock	OK	
T5	外部短絡 / External short circuit	OK	
T6	衝突 (Impact) / 圧壊 (Crush)	OK	
T7	過充電 / Overcharge	OK	single cell は対象外
T8	強制放電 / Forced discharge	OK	

試験実施日 / Tested Date : 2018/12/10~2018/12/24

梱包試験実施日 / Tested Date for Package : 2018/12/14~2018/12/18

上記テスト結果は国連勧告試験(UN Manual of Tests and Criteria 6th, Part III, sub-section 38.3)に従い確認した結果であることを証明いたします。

We, Murata Energy Device Wuxi Co., Ltd., hereby certify that above results are confirmed in accordance with the Manual of Tests and Criteria of the UN Recommendations on the Transport of Dangerous Goods, 6th, Part III, sub-section 38.3.

3) 類似機種とのワット時定格値(Wh)、電圧比率 / Ratios for Watt-hour, Voltage 類似機種に対して、ワット時定格値(Wh)の変化が20%以内、且つ電圧の増加が20%以内であることを証明します。

We certify the change of the subject model to the similar model is in Watt-hour rating of less than 20% and the increase in voltage of less than 20%.

LIS3120 / LIS3119 : ワット時定格値(Wh 比) / Watt-hour Ratio = 100%、

電圧比 / Voltage Ratio = 100%

Weiwei Tang / Manager
CS Quality Assurance Department
Murata Energy Device Wuxi Co., Ltd.

Murata Energy Device Wuxi Co., Ltd.

No.27, Changjiang Road, New District, Wuxi, Jiangsu Province, 214028 P.R.C

Phone: 86-510-8523-9120

Page: 2 of 7

A : Checklist for Judging New Type Cell or not

When there is no change in all items, it is NOT considered to be a New Type Cell.

(Change ⇒ ○、 No change ⇒ -)

Battery Pack Model : LIS3120

Component Cell Model : US508168H5K

Check item	The element which is given influence	Presence of change
Safety parts and mechanical components	Are the safety parts and mechanical components of this cell the same as those of the test completion cell?	—
Cathode material system	Is cathode material system of this cell the same as that of the test completion cell?	—
Anode material system	Is anode material system of this cell the same as that of the test completion cell?	—
Electrolyte material system	Is electrolyte material system of this cell the same as that of the test completion cell?	—
Mass of cathode material	Is mass difference of the design center of each cell concerning cathode less than 20%?	—
Mass of anode material	Is mass difference of the design center of each cell concerning anode less than 20%?	—
Mass of electrolyte	Is mass difference of the design center of each cell concerning electrolyte less than 20%?	—
Judgment result	New Type or not	Not new

Murata Energy Device Wuxi Co., Ltd.

No.27, Changjiang Road, New District, Wuxi, Jiangsu Province, 214028 P.R.C

Phone: 86-510-8523-9120

Page: 3 of 7

B : Checklist for Judging New Type Battery or not

Confirmation of presence of change in "The element which is given influence"

(Change ⇒ O、 No change ⇒ -)

When there is no change in all items, it is NOT considered to be a New Type Battery.

Battery Pack Model : LIS3120

Test Item (Function)	The element which is given influence	Presence of change
T1 : Altitude Simulation (Decompression load)	<ul style="list-style-type: none"> • Crimped part, Gasket (Cell) • Gas Release Vent, Cell Case (Cell) • Pack (Plastic) Case • Holding Member (Insulator, Insulation Tape, Both Sides Tape) • Coating materials 	—
T2 : Thermal Shock (Repetition of high temp. and low temp.)	<ul style="list-style-type: none"> • Crimped part, Gasket (Cell) • Gas Release Vent, Cell Case (Cell) • Finished state of Wound Electrodes (Cell) • Pack (Plastic) Case • Holding Member (Insulator, Insulation Tape, Both Sides Tape) • Coating materials 	—
T3 : Vibration (Vibration load)	<ul style="list-style-type: none"> • Finished state of Wound Electrodes (Cell) • Electric wiring member • Electronic Parts on a circuit board • Cell Holding Member (Adhesive, Both Sides Tape, Lib of Plastic Case) 	—
T4 : Shock (Shock load)	<ul style="list-style-type: none"> • Wiring Member • Electronic Parts on a circuit board • Cell Holding Member (Adhesive, Both Sides Tape, Lib of Plastic Case) • Finished state of Wound Electrodes (Cell) 	—
T5 : External Short Circuit (Short current)	<ul style="list-style-type: none"> • Over-voltage Protection • Current Control Device • Safety Device of cell (Cell) • Lead Tab 	—
T6(Cell) : Impact / Crush (Crash load)	<ul style="list-style-type: none"> • Separator (Cell) • Insulation State in a cell (Cell) 	—
T7(Pack) : Overcharge (Charge load)	<ul style="list-style-type: none"> • Overcharge Protection • Thermal Device • Safety Device of cell (Cell) 	—
T8(Cell) : Forced Discharge (Over discharge load)	<ul style="list-style-type: none"> • Finished state of Wound Electrodes (Cell) 	—
Judgment result	New Type or not	Not new

社外秘 INTERNAL USE ONLY

国联劝告 结果 1

Test Result of UN Recommendations Part 1

机种名/Murata Model Name	LIS3119ACPA		
cell使用/Cell Model Name	US508168H5K	构成/Configuration	1P 3S
试验场所/Test Company	村田新能源(无锡)有限公司		
地址/ Address	中国江苏省无锡市新区长江路27号	电话/Tel	86-18068308951
试验室/Test Room	MDW国联劝告试验室	试验期间/Test Dates	2018.12.10~2018.12.24
判定基准/Criterion	UN Manual of Tests and Criteria Rev6, Part III, sub-section 38.3		

试验名称/Test Name		T1:高度模拟试验				Altitude Simulation		
番号 No.	电池状态 Conditions	试验前／Before		试验后／After		质量减少率／ Mass Loss (0.1%以下)	OCV维持率／ Residual OCV (90%以上)	现象确认／ Occurrence
		Mass(g)	OCV (V)	Mass(g)	OCV (V)			
1	初回满充电/ First cycle, fully charged	224.237	12.878	224.233	12.874	0.00%	100.0%	N
2		224.375	12.880	224.363	12.873	0.01%	99.9%	N
3		223.990	12.885	223.992	12.880	0.00%	100.0%	N
4		224.478	12.897	224.480	12.889	0.00%	99.9%	N
5	50次循环后满充 电/ After 50 cycles, fully charged	224.250	12.907	224.244	12.902	0.00%	100.0%	N
6		224.117	12.888	224.116	12.879	0.00%	99.9%	N
7		224.330	12.905	224.325	12.894	0.00%	99.9%	N
8		224.214	12.904	224.210	12.879	0.00%	99.8%	N

试验名称/Test Name		T2: 温度试验				Thermal		
番号 No.	电池状态 Conditions	试验前／Before		试验后／After		质量减少率／ Mass Loss (0.1%以下)	OCV维持率／ Residual OCV (90%以上)	现象确认／ Occurrence
		Mass(g)	OCV (V)	Mass(g)	OCV (V)			
1	初回满充电/ First cycle, fully charged	224.233	12.874	224.231	12.632	0.00%	98.1%	N
2		224.363	12.873	224.362	12.643	0.01%	98.2%	N
3		223.992	12.880	223.993	12.637	0.00%	98.1%	N
4		224.480	12.889	224.480	12.658	0.00%	98.2%	N
5	50次循环后满充 电/ After 50 cycles, fully charged	224.244	12.902	224.246	12.640	0.00%	98.0%	N
6		224.116	12.879	224.120	12.591	0.00%	97.8%	N
7		224.325	12.894	224.322	12.632	0.00%	98.0%	N
8		224.210	12.879	224.212	12.650	0.00%	98.2%	N

试验名称/Test Name		T3: 振动试验				Vibration		
番号 No.	电池状态 Conditions	试验前/Before		试验后/After		质量减少率/ Mass Loss (0.1%以下)	OCV维持率/ Residual OCV (90%以上)	现象确认/ Occurrence
		Mass(g)	OCV (V)	Mass(g)	OCV (V)			
1	初回满充电/ First cycle, fully charged	224.231	12.632	224.230	12.617	0.00%	99.9%	N
2		224.362	12.643	224.361	12.621	0.00%	99.8%	N
3		223.993	12.637	223.994	12.623	0.00%	99.9%	N
4		224.480	12.658	224.477	12.642	0.00%	99.9%	N
5	50次循环后满充 电/ After 50 cycles, fully charged	224.246	12.640	224.247	12.628	0.00%	99.9%	N
6		224.120	12.591	224.122	12.564	0.00%	99.8%	N
7		224.322	12.632	224.321	12.605	0.00%	99.8%	N
8		224.212	12.650	224.213	12.636	0.00%	99.9%	N

现象/Occurrence	破裂:R <Rupture> 起火:F <Fire> 解体:D <Disassembly> 排气:V <Venting> 渗漏:L <Leakage> 无异常:N <No rupture, No fire, No disassembly, No venting, No leakage>
---------------	--

国联劝告试验 结果 2

Test Result of UN Recommendations Part 2

No: MDW-PC1825

DATE: 2018.12.25

PAGE: 5 of 7 Page

试验名称/Test Name		T4: 冲击试验				Shock		
番号 No.	电池状态 Conditions	试验前/Before		试验后/After		质量减少率/ Mass Loss (0.1%以下)	OCV维持率/ Residual OCV (90%以上)	现象确认/ Occurrence
		Mass(g)	OCV (V)	Mass(g)	OCV (V)			
1	初回满充电/ First cycle, fully charged	224.230	12.617	224.230	12.613	0.00%	100.0%	N
2		224.361	12.621	224.362	12.622	0.00%	100.0%	N
3		223.994	12.623	223.994	12.623	0.00%	100.0%	N
4		224.477	12.642	224.477	12.640	0.00%	100.0%	N
5	50次循环后满充 电/ After 50 cycles, fully charged	224.247	12.628	224.247	12.625	0.00%	100.0%	N
6		224.122	12.564	224.122	12.563	0.00%	100.0%	N
7		224.321	12.605	224.321	12.604	0.00%	100.0%	N
8		224.213	12.636	224.212	12.635	0.00%	100.0%	N
现象/Occurrence		破裂:R <Rupture> 起火:F <Fire> 解体:D <Disassembly> 排气:V <Venting> 渗漏:L <Leakage> 无异常:N <No rupture, No fire, No disassembly, No venting, No leakage>						
试验名称/Test Name		T5: 外短路试验				External Short Circuit		
番号 No.	电池状态 Conditions	最大表面温度/Max. Surface Temperature (°C) 170°C	现象确认/ Occurrence	番号 No.	电池状态 Conditions	最大表面温度/Max. Surface Temperature (°C) 170°C	现象确认/ Occurrence	
1	初回满充电/ First cycle, fully charged	55.4°C	N	5	50次循环后满充电 / After 50 cycles, fully charged	55.5°C	N	
2		55.6°C	N	6		55.4°C	N	
3		55.7°C	N	7		55.3°C	N	
4		55.7°C	N	8		55.3°C	N	
现象/Occurrence		破裂:R <Rupture> 起火:F <Fire> 解体:D <Disassembly> 无异常:N <No rupture, No fire, No disassembly>						
试验名称/Test Name		T6: 撞击(impact)/挤压(crush) 试验						
番号 No.	电池状态 Conditions	最大表面温度/Max. Surface Temperature (°C) 170°C			现象确认/Occurrence			
1	初回 50%充电 (宽面)/ First cycle, 50% charged (wide surface)	<160°C			N			
2		<160°C			N			
3		<160°C			N			
4		<160°C			N			
5		<160°C			N			
现象/Occurrence		解体: D <Disassembly> 起火: F <Fire> 无异常: N <No fire, No disassembly>						
试验名称/Test Name		T7: 过充电试验				Overcharge		
番号 No.	电池状态 Conditions	现象确认/Occurrence		番号 No.	电池状态 Conditions	现象确认/Occurrence		
1	初回满充电/ First cycle, fully charged	N		5	50次循环后 满充电/ After 50 cycles, fully charged	N		
2		N		6		N		
3		N		7		N		
4		N		8		N		
现象/Occurrence		起火: F <Fire> 解体: D <Disassembly> 无异常: N <No fire, No disassembly>						

* Temperature Measurement by Thermolabel

No.: MDW-PC1825

DATE: 2018.12.25

PAGE: 6 of 7 Page

国联劝告试验 结果 3

Test Result of UN Recommendations Part 3

社外秘 INTERNAL
USE ONLY

试验名称 /Test Name		T8: 强制放电 Forced Discharge			
番号 No.	电池状态 Conditions	现象确认 /Occurrence	番号 No.	电池状态 Conditions	现象确认 /Occurrence
1	初次循环 完全放电 / First cycle, fully discharged	N	11	50次循环后 完全放电 / After 50 cycles, fully discharged	N
2		N	12		N
3		N	13		N
4		N	14		N
5		N	15		N
6		N	16		N
7		N	17		N
8		N	18		N
9		N	19		N
10		N	20		N
现象 / Occurrence		起火:F <Fire> 解体:D <Disassembly> 无异常:N <No fire, No disassembly>			

社外秘 INTERNAL USE ONLY

国連勧告試験 梱包結果


Test Result of UN Recommendations for Package

No : MDW-PC1825

DATE 2018.12.25

PAGE 7 of 7
Page

試験場所/ Test Company	村田新能源(无锡)有限公司			
地址/ Address	中国江苏省无锡市新区长江路27号		電話/ Tel	86-18068308951
試験室/ Test Room	MDW国联劝告試験室	試験期間/ Test Dates	2018.12.14~2018.12.18	試験番号/ Test No
機種名/ Murata Model Name	LIS3119ACPA		梱包入数/ Quantity	30 pcs
使用セル/ Cell Model Name	US508168H5K	構成/ Configuration	1P3S	梱包製造所/ Package Factory
包装等級/ Packing Group	等級 II / Packing Group Number II			
寸法・質量/ Dimensions and Gross Weight	長辺/Length (L)	短辺 /Wide (W)	高度/Height (H)	質量 /Gross Weight (kg)
	359 mm	267 mm	160 mm	8.8 kg

■ 落下試験/Drop Test					
試験設備		虹創力 HD-S015			
試験条件/ Test condition		落下高度 /Drop height	1.2m	試験結果 /Occurrence	
<div>落下姿勢(方向)/ Five (one for each drop)</div> 		第1回落下試験	底面水平向下/ flat on the bottom	著しい破損なし/No Leakage, No damage liable to affect safety during	
		第2回落下試験	頂面水平向下 / flat on the top	著しい破損なし/No Leakage, No damage liable to affect safety during	
		第3回落下試験	長側面水平向下/ flat on the long side	著しい破損なし/No Leakage, No damage liable to affect safety during	
		第4回落下試験	短側面水平向下/ flat on the short side	著しい破損なし/No Leakage, No damage liable to affect safety during	
		第5回落下試験	一角向下※/ on a corner	著しい破損なし/No Leakage, No damage liable to affect safety during	
		※一角：选择容器最易受损的方向			
判定基準/ Criterion		Each package must be capable of withstanding a 1.2m drop test in any orientation without : ・ Damage to cells or batteries contained therein; ・ Shifting of contents so as to allow battery(or cell to cell) contact ・ Release of contents		判定/ Judgment	合格/OK

■ 積み重ね試験/Stacking Test				
試験条件/Test condition	No	試験結果 /Occurrence		
試験荷重値/Weight Load	160 kg	1	漏洩・破損・歪みなし/No leakage, No distortion, No deterioration	
		2	漏洩・破損・歪みなし/No leakage, No distortion, No deterioration	
		3	漏洩・破損・歪みなし/No leakage, No distortion, No deterioration	
判定基準/ Criterion	試験品は漏洩があつてはならない。試験品は、輸送の安全性を損なうような劣化、又はその強度を減じたり、又は輸送物の積み重ねを不安定にするような歪みが生じてはならない。		判定/ Judgment	合格/OK

村田新能源
(无锡)有限公司
Wei Wei Tang / ManagerCS Quality Assurance Department
Murata Energy Device WuXi Co., Ltd.

品保-P检-022(4)

総合判定

合格/OK

社外秘 | INTERNAL
USE ONLY

1. 2m落下試験写真／1. 2mDrop Test Photo

リチウムイオン電池／lithium-ion cell or battery

ムラタ機種名／Murata model name: LIS3119ACPA

Before



After



社外秘 | INTERNAL
USE ONLY

積み重ね試験写真／/Stacking Test Photo

リチウムイオン電池／lithium-ion cell or battery

ムラタ機種名／Murata model name: LIS3119ACPA

Before



After

